



# nomalen® 28N

<u>Property</u>	<u>Typical value</u>	<u>Norm</u>
Density	28 kg/m <sup>3</sup>	DIN 53420
Tensile Strength //	23 N/cm <sup>2</sup>	ISO 1798
Tensile Strength ⊥	28 N/cm <sup>2</sup>	ISO 1798
Elongation //	103 %	ISO 1798
Elongation ⊥	101 %	ISO 1798
Compressive Strength, deflection 25%	45 kPa	ISO 3386
Compressive Strength, deflection 50%	105 kPa	ISO 3386
Water absorption 24d	<1,0 vol.-%	DIN 53428
Recommended working temperature	-50 - +95°C	
Thermal conductivity	on request	
Fire behaviour	on request	

This information is based on our actual knowledge. However, it does not constitute a guarantee of our product's characteristics and does not engage in any case our liability.

## NMC Termonova Oy

Torppanummentie 44, FI-10210 Inkoo, Finland,

Tel.: + 358 (0)207 809600, Fax: + 358 (0)207 809601, e-mail: [info@termonova.fi](mailto:info@termonova.fi), [www.termonova.fi](http://www.termonova.fi)

Y-tunnus/ FO-nummer/ business ID 0114914-9 ALV/Moms/ VAT FI01149149

